



RAND YORK MINERALS (PTY) LTD

Reg. No. 1985/004951/07

Tel: +27 (11) 463 9000
Fax: +27 (11) 463 7002
Email: randyork@mweb.co.za

PO Box 650755
Benmore, 2010
South Africa

Lumpy Chrome Ore *Data Sheet*

Specification:

Cr ₂ O ₃	34 - 37 %	typical range
SiO ₂	14.0	% max (typ 11 - 13% range)
Cr/Fe	1.45 : 1	min (typ 1.48 - 1.52 range)
FeO	30.0	% max (typ 23 - 26% range)
MgO	12.0	% max (typ 9.90 - 11% range)
Al ₂ O ₃	17.0	% max (typ 14.50-15.50% range)
CaO	1.00	% max (typ 0.35 - 0.45% range)
P	0.02	% max (typ 0.003%)
S	0.015	% max (typ 0.003%)

Size:

Approx 5 - 150mm. Typically 10% below and max 5% above at time of container loading. Not responsible for any generation of fines during transport.